
आपूर्ति गर्ने सेनिटरी प्याडहरुको गुणस्तर सेनिटरी प्याड (वितरण तथा व्यवस्थापन) कार्यविधि, २०७६ को अनुसुचि १ अनुसार देहाय बमोजिम हुनुपर्नेछ ।

e and physical finishing: Regular with wing, napkin with uniform thickness ughout without any wrinkles and distortion. The sanitary napkins shall have a soft and when worn shall not chafe or give any uncomfortable feeling. They shall be free all sorts of foreign matter.
Material permitted:  a. Absorbent filter: plant-based raw materials such as wood pulp, cellulose pulp, bamboo fiber, banana fiber and corn which have natural sterilization effects, tissue paper, pure cotton, shall be free from lumps, oil spots, dirt or foreign maternal.  b. Covering: The covering of the absorbent filter shall be of a good quality cotton or rayon knitted sleeving, gauze or non-woven fabric with sufficient porosity to permit the assembled pad to meet absorbency requirements.
e: size including minimum 240±20 mm length and 60 to 75 mm width, thickness mm ±2 mm
orbency: the sanitary pad shall absorb at least 30 ml of colored distiled water and it l not show leakage at the bottom or sides of the sanitary napkin.
posability: disposable pad with the covering removed, shall be immersed in 15 liters vater and stirred. The pad shall disintegrate in the water in not more than 5 minutes.
or: The product shall be white in color and shall be almost ne odourless.
value: free from acid and alkali, pH of absorbent material shall be 6-8.5 (tested as the method given in Indian Standard 1390)
giene testing requirement: Total viable count (total number of bacteria and fungi)  I be not more than 1000 cfu/gm and absence of Staphylococcus aureus. The napkin  I be tested for the presence of staphylococcus aureus in accordance with IS 5887 (Part
manufacturer shall declare that all ingredients used in the product are safe for human ed on its known toxicological characteristics at intended use.
king type: at least 90% Compostable Pack, Protecting Package to product.
kaging size: Minimum 8 pads per pack.
odegradability or Composability requirements: At least 90% degrade within 6 nth (testing is performed and conformed from recognized and approved laboratory.
cl



विशो गाउपासकी मिलाको कार्यास के, कार्यिकार प्रवेश, नवास